

THOMSON
DELPHION

RESEARCH



PRODUCTS

INSIDE DELPHION

My Account | Products

Search: Quick/Number Boolean Advanced Derwent

The Delphion Integrated View

Get Now: ☒ PDF | [More choices...](#)Tools: Add to Work File: [Create new Work File](#)View: [INPADOC](#) | Jump to: [Top](#)  Go to: [Derwent](#) [Email this to a](#)Title: **JP58128652A2: MANUFACTURE OF SEPARATOR FOR ALKALINE BATTEI**Derwent Title: Heat resistant alkaline battery separator - with film obtd. by mixing polyolefin with extracted substance and nonionic surfactant. NoAbstract
[\[Derwent Record\]](#)Country: **JP Japan**Kind: **A**Inventor: **SAWAZAKI TAKASHI;
NOJIRI AKIO;**Assignee: **FURUKAWA ELECTRIC CO LTD:THE
FURUKAWA BATTERY CO LTD:THE**
[News, Profiles, Stocks and More about this company](#)Published / Filed: **1983-08-01 / 1982-01-27**Application Number: **JP1982000011111**IPC Code: **H01M 2/16;**Priority Number: **1982-01-27 JP1982000011111**Abstract: **PURPOSE:** To obtain a separator for an alkaline battery which has a good charge-and-discharge life characteristic by mixing a polyolefin with an extracted matter and a nonionic surface active agent, forming the mixture into a film, and subjecting the film to extraction treatment.**CONSTITUTION:** After 55 parts of paraffin with a melting point of 68~71°C, 8 parts of a fatty-acid-amide-system surfactant and 0.5 parts of hindered-phenol- system antioxidant are added to 100 parts of ethylene-propylene block copolymer (containing 13wt% of ethylene) with a melt index of 0.3, the mixture is kneaded with a kneader at a resin temperature of about 180°C for 20min. Next, after the kneaded mixture is formed into a film with 40μ thickness by means of an electric heating press, the film is subjected to extraction treatment by being immersed in benzene at ordinary temperature for 16hr. After that, the film is dried. By the means mentioned above, an alkali-proof alkali-oxidation-proof heat-proof separator which has excellent electric and mechanical characteristics and has a low cost, can be obtained. Consequently, the charge-and-discharge life characteristic of an alkaline battery can be enhanced by using such a separator.**COPYRIGHT:** (C)1983,JPO&JapioFamily: **None**Other Abstract Info: **None****Best Available Copy**



[Nominate](#)



[this for the Gallery...](#)

© 1997-2004 Thomson

[Research Subscriptions](#) | [Privacy Policy](#) | [Terms & Conditions](#) | [Site Map](#) | [Contact Us](#) | [Help](#)



(19)

(11) Publication number: **581286**

Generated Document.

PATENT ABSTRACTS OF JAPAN(21) Application number: **57011111**(51) Intl. Cl.: **H01M 2/16**(22) Application date: **27.01.82**

(30) Priority:

(43) Date of application
publication: **01.08.83**(84) Designated contracting
states:(71) Applicant: **FURUKAWA ELECTRIC CO
LTD:THE
FURUKAWA BATTERY CO
LTD:THE**(72) Inventor: **SAWAZAKI TAKASHI
NOJIRI AKIO**

(74) Representative:

**(54) MANUFACTURE OF
SEPARATOR FOR
ALKALINE BATTERY**

(57) Abstract:

PURPOSE: To obtain a separator for an alkaline battery which has a good charge-and-discharge life characteristic by mixing a polyolefin with an extracted matter and a nonionic surface active agent, forming the mixture into a film, and subjecting the film to extraction treatment.

CONSTITUTION: After 55 parts of paraffin with a melting point of 68 ~ 71°C, 8 parts of a fatty-acid-amide-system surfactant and 0.5 parts of hindered-phenol- system antioxidant are added to 100 parts of ethylene-propylene block copolymer (containing 13wt% of ethylene) with a melt index of 0.3, the mixture is kneaded with a kneader at a resin temperature of about 180°C for 20min. Next, after the kneaded mixture is

formed into a film with 40μ thickness by means of an electric heating press, the film is subjected to extraction treatment by being immersed in benzene at ordinary temperature for 16hr. After that, the film is dried. By the means mentioned above, an alkali-proof alkali-oxidation-proof heat-proof separator which has excellent electric and mechanical characteristics and has a low cost, can be obtained. Consequently, the charge-and-discharge life characteristic of an alkaline battery can be enhanced by using such a separator.

COPYRIGHT: (C)1983,JPO&Japio